

740plus

680plus

0.22

0.11

0.055

0.042

0.028

220plus

190plus

Forms of delivery

Sheets, ex warehouse

Thickness: 12.5 and 25 mm Length: 1,500 mm Width: 1,000 mm

Customized strips and pads, self-adhesive versions and special roll lengths available on request.

Technical details

Maximum static load bearing capacity

 $2.500\ N/mm^2$

Maximum dynamic load bearing capacity for intermitted loadings


0 to 3.500 N/mm²

Rare, short term peak loads

up to 8.000 N/mm²


Certification

Cradle to Cradle Certified® is a registered trademark of the Cradle to Cradle Products Innovation Institute.





Physical property	Norm	Result	Comment	0.018	
Static modulus of elasticity	Based on EN 826	20.0 - 78.0 N/mm²	Tangential modulus, see figure "modulus of elasticity"	0.011	7
Dynamic modulus of elasticity	Based on DIN 53513	41.0 - 160.0 N/mm²	Depending on frequency, load and thickness, see figure "dynamic stiffness"	0.00	1001
Mechanical loss factor	DIN 53513	0.09	Load-, amplitude- and frequency-dependent	N/mr	TI ²
Compression set	Based on DIN EN ISO 1856	8.6 %	Measured 30 minutes after decompression with 50 % deformation / 23 °C after 72 hrs	-	
Tensile strength	Based on DIN EN ISO 1798	6.9 N/mm²		=	
Elongation at break	Based on DIN EN ISO 1798	190 %		-	
Tear resistance	Based on DIN ISO 34-1	34.5 N/mm		-	
Fire behaviour	DIN 4102 DIN EN 13501-1	B2 E		=	
Sliding friction	REGUPOL-laboratory REGUPOL-laboratory	0.5 0.6	Steel (dry) Concrete (dry)	-	
Compression hardness	Based on DIN EN ISO 3386-2	3 640 kPa	Compressive stress at 25 % deformation test specimen h = 25 mm	-	
Rebound elasticity	Based on DIN EN ISO 8307	55 %	dependent on thickness, test specimen h = 25 mm	-	
Force reduction	DIN EN 14904	20 %	dependent on thickness, test specimen h = 25 mm	-	





Examination of deflection in accordance to DIN EN 826 between two stiff panels. Illustration based on the third loading. Velocity of loading and unloading 20 seconds. Tested at room temperature. Dimensions of test specimens 125×125 mm.





Illustration of the isolation efficiency of a single-degree-of-freedom system (SDOF system) on a rigid base with **REGUFOAM vibration 990 plus.** Parameter: power transmission (insertion loss) in dB, isolation factor in %.



Natural frequency of a single-degree-of-freedom system (SDOF system) considering the dynamic stiffness of **REGUFOAM vibration 990plus** on a rigid base. Dimensions of test specimens 125×125 mm.

 N/mm^2

2.50

Influence of Amplitude

In order to get information of changes in mechanical loss or dynamic stiffness due to changes in amplitudes please ask technical staff of **REGUPOL**.




Illustration of the dynamic modulus of elasticity for sinusoidal excitation at a constant mean load and an amplitude of \pm 0.10 mm. Dimensions of specimens 125 x 125 x 25 mm; static modulus of elasticity as a result of the tangent modulus of the spring characteristic. Tested in accordance with DIN 53513.




Illustration of the dynamic stiffness for sinusoidal excitation at a constant mean load and an amplitude of \pm 0.10 mm. Dimensions of specimens 125 x 125 x 25 mm; static stiffness as a result of the tangent modulus of the spring characteristic. Tested in accordance with DIN 53513.

2.50

740plus

680plus

300plus


220plus

190plus

150plus

0.00

N/mm²



Dimensions of specimens 125 x 125 x 50 mm

Exclusion of Liability

Technical services and offers based on these are subject to our General Terms and Conditions of sale, a copy of which can be found on our website www.regupol.com. Special attention should be paid to paragraphs 4 and 5. In so far, please be advised as follows:

Our expertise is the development and manufacturing of products. With our recommendation we can only assist you in selecting a product that is suitable for your demand. However, we cannot act as your architect or consulting expert. This would only be possible subject to a separately concluded service contract that we would have to bill you

for. Such contracts are not part of our scope of supply and services. Hence, our recommendation does not lay claim for its correctness. Guarantees do only apply to the technical properties of the material supplied.

Comment on tolerances: All technical values correspond to our current state of knowledge and are to be understood as reference values only. These values can be subject to considerable variabilities due to production and/or material reasons as well as due to outside influences (temperature, humidity etc.). Thus special agreements on material parameters might be necessary on a case-by-case basis.